



# YUPO® FEB-150 Specification Sheet

## Accel® 78 lb.Text

<u>Parameter</u>	<u>Units</u>	<u>Range</u>	<u>Reference*</u>	<u>Notes</u>
Thickness, Average	micron	150 +/- 5	JIS P-8118	2
Basis Weight, Average	g/m2	115.5 +/- 5.0	JIS P-8124	2
Opacity, Average	%	95.5 min.	TAPPI T-425	2
Gloss, Average - Top	%	48 +/- 10	TAPPI T-480	2
- Back	%	47 +/- 10	TAPPI T-480	2
Whiteness, Average	WI	95 min.	JIS L-1015	2

### Notes Key:

2 - Specification range shown

\* Yupo test methods based on, but not necessarily the same as, reference stated; Yupo procedure stated if reference not available.

This document provides our current specifications for FEB-150. Changes to these items may occur at the sole discretion of Yupo Corporation America. This issue supersedes any and all previous versions.

FEB-150, version 4, 2012-Jun-14