



# Yupoilluminat® FPU250 Specification Sheet

## UV Inkjet

<u>Parameter</u>	<u>Units</u>	<u>Range</u>	<u>Reference*</u>	<u>Notes</u>
Thickness, Average	micron	250 +/- 12	JIS P-8118	2
Basis Weight, Average	g/m2	200.0 +/- 9.0	JIS P-8124	2
Opacity, Average	%	98.0 min.	TAPPI T-425	2
Gloss, Average - Top	%	18 +/- 4	TAPPI T-480	2
Gloss, Average - Back	%	18 +/- 4	TAPPI T-480	2
Whiteness, Average	WI	96 +/- 2	JIS L-1015	2
Surface Resistivity - Top	log( $\Omega/\square$ )	12.0 max.	ASTM D257	2
Surface Resistivity - Back	log( $\Omega/\square$ )	12.0 max.	ASTM D257	2
Tensile Strength - MD	kgf/15mm	11.5 min.	TAPPI T-494	2
Tensile Strength - TD	kgf/15mm	40.0 min.	TAPPI T-494	2
5% Elongation - MD	kgf/15mm	6.5 +/- 1.5	TAPPI T-494	2
5% Elongation - TD	kgf/15mm	20.0 +/- 4.0	TAPPI T-494	2
Tear Strength - MD	gf	160.0 +/- 20.0	TAPPI T-414	2
Tear Strength - TD	gf	64.0 +/- 29.0	TAPPI T-414	2
Clark Stiffness - MD	s-value	124.0 min.	TAPPI T-451	1,2
Clark Stiffness - TD	s-value	235.0 min.	TAPPI T-451	1,2

### Notes Key:

1 - Stiffness increases with aging over the first month from date of manufacture.

2 - Specification range shown

\* Yupo test methods based on, but not necessarily the same as, reference stated; Yupo procedure stated if reference not available.

This document provides our current specifications for FPU250. Changes to these items may occur at the sole discretion of Yupo Corporation America. This issue supersedes any and all previous versions.

FPU250, version 5, 2014-Jun-24