



YUPO® HJG-070 Specification Sheet

37 lb. Text

<u>Parameter</u>	<u>Units</u>	<u>Range</u>	<u>Reference*</u>	<u>Notes</u>
Thickness, Average		70 +/- 4	JIS P-8118	2
Basis Weight, Average		55.0 +/- 3.0	JIS P-8124	2
Opacity, Average		85.0 min.	TAPPI T-425	2
Gloss, Average - Top		17 +/- 4	TAPPI T-480	2
- Back		17 +/- 4	TAPPI T-480	2
Whiteness, Average		96 +/- 2	JIS L-1015	2
Surface Resistivity - Top	log(Ω/\square)	12.0 max.	ASTM D257	2
- Back	log(Ω/\square)	12.0 max.	ASTM D257	2
Tensile Strength - MD		3.8 min.	TAPPI T-494	2
- TD		10.0 min.	TAPPI T-494	2
5% Elongation - MD		2.0 +/- 1.0	TAPPI T-494	2
- TD		5.0 +/- 2.0	TAPPI T-494	2
Tear Strength - MD		21.0 +/- 10.0	TAPPI T-414	2
- TD		11.7 +/- 8.0	TAPPI T-414	2
Clark Stiffness - MD		6.7 min.	TAPPI T-451	1, 2
- TD		18.0 min.	TAPPI T-451	1, 2

Notes Key:

- 1 - Stiffness increases with aging over the first month from date of manufacture.
- 2 - Specification range shown

* Yupo test methods based on, but not necessarily the same as, reference stated; Yupo procedure stated if reference not available.

This document provides our current specifications for HJG-070. Changes to these items may occur at the sole discretion of Yupo Corporation America. This issue supersedes any and all previous versions.