



YUPO® IZE-105 Specification Sheet

IML Z Grade (PP Adhesive)

<u>Parameter</u>	<u>Units</u>	<u>Range</u>	<u>Reference*</u>	<u>Notes</u>
Thickness, Average	micron	107 +/- 7	JIS P-8118	2
Basis Weight, Average	g/m2	82.7 +/- 4.0	JIS P-8124	2
Opacity, Average	%	92.0 min.	TAPPI T-425	2
Gloss, Average - Adhesive	%	30 +/- 8	TAPPI T-480	2
- Print Side	%	22 +/- 4	TAPPI T-480	2
Whiteness, Average	WI	94 min.	JIS L-1015	2
Surface Resistivity - Adhesive	log(Ω/\square)	14.0 max.	ASTM D257	2
- Print Side	log(Ω/\square)	13.0 max.	ASTM D257	2
Tensile Strength - MD	kgf/15mm	4.0 min.	TAPPI T-494	2
- TD	kgf/15mm	12.5 min.	TAPPI T-494	2
5% Elongation - MD	kgf/15mm	2.4 +/- 1.0	TAPPI T-494	2
- TD	kgf/15mm	7.0 +/- 3.0	TAPPI T-494	2
Tear Strength - MD	gf	35.0 +/- 9.0	TAPPI T-414	2
- TD	gf	18.3 +/- 7.2	TAPPI T-414	2
Clark Stiffness - MD	s-value	11.0 min.	TAPPI T-451	1, 2
- TD	s-value	32.0 min.	TAPPI T-451	1, 2

Notes Key:

- 1 - Stiffness increases with aging over the first month from date of manufacture.
- 2 - Specification range shown

* Yupo test methods based on, but not necessarily the same as, reference stated; Yupo procedure stated if reference not available.

This document provides our current specifications for IZE-105. Changes to these items may occur at the sole discretion of Yupo Corporation America. This issue supersedes any and all previous versions.