



Yupo® Original QJJ400 Specification Sheet

144 LB Cover 15.7 PT

<u>Parameter</u>	<u>Units</u>	<u>Range</u>	<u>Reference*</u>	<u>Notes</u>
Thickness, Average	micron	400 +/- 16	JIS P-8118	2
Basis Weight, Average	g/m2	390.0 +/- 16.0	JIS P-8124	2
Opacity, Average	%	94.5 min.	TAPPI T-425	2
Gloss, Average - Top	%	21 +/- 6	TAPPI T-480	2
Gloss, Average - Back	%	21 +/- 6	TAPPI T-480	2
Whiteness, Average	WI	94 min.	JIS L-1015	2

Notes Key:

2 - Specification range shown

* Yupo test methods based on, but not necessarily the same as, reference stated; Yupo procedure stated if reference not available.

This document provides our current specifications for QJJ400. Changes to these items may occur at the sole discretion of Yupo Corporation America. This issue supersedes any and all previous versions.

QJJ400, version 3, 2012-Jun-15