



# YUPO® WKFS-340 Specification Sheet

## YUPO Octopus® OS - Sheet Offset

<u>Parameter</u>	<u>Units</u>	<u>Range</u>	<u>Reference*</u>	<u>Notes</u>
Thickness, Average	micron	330 +/- 35	JIS P-8118	2
Basis Weight, Average	g/m2	210.0 +/- 24.0	JIS P-8124	2
Gloss, Average - Printsides	%	53 +/- 6	TAPPI T-480	2
Whiteness, Average	WI	94 min.	JIS L-1015	2

### Notes Key:

2 - Specification range shown

\* Yupo test methods based on, but not necessarily the same as, reference stated; Yupo procedure stated if reference not available.

This document provides our current specifications for WKFS-340. Changes to these items may occur at the sole discretion of Yupo Corporation America. This issue supersedes any and all previous versions.

WKFS-340, version 2, 2014-Feb-06