



YUPO Octopus® OS WKFS340 Specification Sheet

Sheet Offset

<u>Parameter</u>	<u>Units</u>	<u>Range</u>	<u>Reference*</u>	<u>Notes</u>
Thickness, Average	micron	330 +/- 35	JIS P-8118	2
Basis Weight, Average	g/m2	210.0 +/- 24.0	JIS P-8124	2
Gloss, Average - Printsides	%	53 +/- 6	TAPPI T-480	2
Whiteness, Average	WI	94 min.	JIS L-1015	2
Whiteness, Average	WI	94 min.	JIS L-1015	2

Notes Key:

2 - Specification range shown

* Yupo test methods based on, but not necessarily the same as, reference stated; Yupo procedure stated if reference not available.

This document provides our current specifications for WKFS340. Changes to these items may occur at the sole discretion of Yupo Corporation America. This issue supersedes any and all previous versions.

WKFS340, version 2, 2014-Feb-06