



Yupo Accel® FEB130 Specification Sheet 68 LB Text 5.1 PT

| <u>Parameter</u> | <u>Units</u> | <u>Range</u> | <u>Reference*</u> | <u>Notes</u> |
|-----------------------|--------------|---------------|-------------------|--------------|
| Thickness, Average | micron | 130 +/- 5 | JIS P-8118 | 2 |
| Basis Weight, Average | g/m2 | 100.1 +/- 5.0 | JIS P-8124 | 2 |
| Opacity, Average | % | 95.0 min. | TAPPI T-425 | 2 |
| Gloss, Average - Top | % | 45 +/- 10 | TAPPI T-480 | 2 |
| Gloss, Average - Back | % | 45 +/- 10 | TAPPI T-480 | 2 |
| Whiteness, Average | WI | 95 min. | JIS L-1015 | 2 |

Notes Key:

2 - Specification range shown

* Yupo test methods based on, but not necessarily the same as, reference stated; Yupo procedure stated if reference not available.

This document provides our current specifications for FEB130. Changes to these items may occur at the sole discretion of Yupo Corporation America. This issue supersedes any and all previous versions.

FEB130, version 6, 2016-Jul-26