



Yupo Accel® FEB150 Specification Sheet 78 LB Text 5.9 PT

<u>Parameter</u>	<u>Units</u>	<u>Range</u>	<u>Reference*</u>	<u>Notes</u>
Thickness, Average	micron	150 +/- 5	JIS P-8118	2
Basis Weight, Average	g/m2	115.5 +/- 5.0	JIS P-8124	2
Opacity, Average	%	95.5 min.	TAPPI T-425	2
Gloss, Average - Top	%	48 +/- 10	TAPPI T-480	2
Gloss, Average - Back	%	47 +/- 10	TAPPI T-480	2
Whiteness, Average	WI	95 min.	JIS L-1015	2

Notes Key:

2 - Specification range shown

* Yupo test methods based on, but not necessarily the same as, reference stated; Yupo procedure stated if reference not available.

This document provides our current specifications for FEB150. Changes to these items may occur at the sole discretion of Yupo Corporation America. This issue supersedes any and all previous versions.

FEB150, version 4, 2012-Jun-14