



Yupo Accel® FEB250 Specification Sheet 74 LB Cover 9.9 PT

<u>Parameter</u>	<u>Units</u>	<u>Range</u>	<u>Reference*</u>	<u>Notes</u>
Thickness, Average	micron	250 +/- 10	JIS P-8118	2
Basis Weight, Average	g/m2	200.0 +/- 9.0	JIS P-8124	2
Opacity, Average	%	98.0 min.	TAPPI T-425	2
Gloss, Average - Top	%	45 +/- 9	TAPPI T-480	2
Gloss, Average - Back	%	45 +/- 9	TAPPI T-480	2
Whiteness, Average	WI	95 min.	JIS L-1015	2

Notes Key:

2 - Specification range shown

* Yupo test methods based on, but not necessarily the same as, reference stated; Yupo procedure stated if reference not available.

This document provides our current specifications for FEB250. Changes to these items may occur at the sole discretion of Yupo Corporation America. This issue supersedes any and all previous versions.

FEB250, version 4, 2012-Jun-15