



YUPO[®] Original FIG350 Technical Data Sheet

100 LB Cover 13.8 PT

<u>Parameter</u>	<u>Units</u>	<u>Range</u>	<u>Reference*</u>	<u>Notes</u>
Thickness, Average	micron	350 +/- 16	JIS P-8118	2
Basis Weight, Average	g/m ²	271.5 +/- 11.0	JIS P-8124	2
Opacity, Average	%	98.0 min.	TAPPI T-425	2
Gloss, Average - Top	%	19 +/- 4	TAPPI T-480	2
Gloss, Average - Back	%	32 +/- 4	TAPPI T-480	2
Whiteness, Average	WI	95.0 +/- 2.0	JIS L-1015	2

Notes Key:

2 - Specification range shown

* YUPO test methods based on, but not necessarily the same as, reference stated; YUPO procedure stated if reference not available.

This document provides our current specifications for FIG350. Changes to these items may occur at the sole discretion of Yupo Corporation America. This issue supersedes any and all previous versions.

FIG350, version 15, Issue date 2020-Jul-20