



Yupo® Original FPG150 Specification Sheet

78 LB Text 5.9 PT

<u>Parameter</u>	<u>Units</u>	<u>Range</u>	<u>Reference*</u>	<u>Notes</u>
Thickness, Average	micron	150 +/- 8	JIS P-8118	2
Basis Weight, Average	g/m2	115.5 +/- 5.0	JIS P-8124	2
Opacity, Average	%	95.0 min.	TAPPI T-425	2
Gloss, Average - Top	%	20 +/- 4	TAPPI T-480	2
Gloss, Average - Back	%	20 +/- 4	TAPPI T-480	2
Whiteness, Average	WI	96 +/- 2	JIS L-1015	2
Surface Resistivity - Top	log(Ω/\square)	12.0 max.	ASTM D257	2
Surface Resistivity - Back	log(Ω/\square)	12.0 max.	ASTM D257	2
Tensile Strength - MD	kgf/15mm	9.0 min.	TAPPI T-494	2
Tensile Strength - TD	kgf/15mm	25.0 min.	TAPPI T-494	2
5% Elongation - MD	kgf/15mm	4.4 +/- 1.4	TAPPI T-494	2
5% Elongation - TD	kgf/15mm	12.0 +/- 3.0	TAPPI T-494	2
Tear Strength - MD	gf	63.0 +/- 17.0	TAPPI T-414	2
Tear Strength - TD	gf	31.0 +/- 11.0	TAPPI T-414	2
Clark Stiffness - MD	s-value	48.0 min.	TAPPI T-451	1,2
Clark Stiffness - TD	s-value	106.0 min.	TAPPI T-451	1,2

Notes Key:

1 - Stiffness increases with aging over the first month from date of manufacture.

2 - Specification range shown

* Yupo test methods based on, but not necessarily the same as, reference stated; Yupo procedure stated if reference not available.

This document provides our current specifications for FPG150. Changes to these items may occur at the sole discretion of Yupo Corporation America. This issue supersedes any and all previous versions.

FPG150, version 23, 2014-Jun-24