



YUPO[®] Original FPG250 Technical Data Sheet

74 LB Cover 9.9 PT

<u>Parameter</u>	<u>Units</u>	<u>Range</u>	<u>Reference*</u>	<u>Notes</u>
Thickness, Average	micron	250 +/- 12	JIS P-8118	2
Basis Weight, Average	g/m ²	200.0 +/- 9.0	JIS P-8124	2
Opacity, Average	%	98.0 min.	TAPPI T-425	2
Gloss, Average - Top	%	18 +/- 4	TAPPI T-480	2
Gloss, Average - Back	%	18 +/- 4	TAPPI T-480	2
Whiteness, Average	WI	96.0 +/- 2.0	JIS L-1015	2

Notes Key:

2 - Specification range shown

* YUPO test methods based on, but not necessarily the same as, reference stated; YUPO procedure stated if reference not available.

This document provides our current specifications for FPG250. Changes to these items may occur at the sole discretion of Yupo Corporation America. This issue supersedes any and all previous versions.

FPG250, version 23, Issue date 2020-Jul-20