



YUPOBlue® YPBL250 Specification Sheet

74 LB Cover 9.9 PT - HP® Indigo

<u>Parameter</u>	<u>Units</u>	<u>Range</u>	<u>Reference*</u>	<u>Notes</u>
Thickness, Average	micron	250 +/- 10	JIS P-8118	2
Basis Weight, Average	g/m2	200.0 +/- 9.0	JIS P-8124	2
Opacity, Average	%	98.0 min.	TAPPI T-425	2
Gloss, Average - Top	%	15 +/- 8	TAPPI T-480	2
Gloss, Average - Back	%	15 +/- 8	TAPPI T-480	2
Whiteness, Average	WI	93 min.	JIS L-1015	2
Tensile Strength - MD	kgf/15mm	11.5 min.	TAPPI T-494	2
Tensile Strength - TD	kgf/15mm	41.0 min.	TAPPI T-494	2
5% Elongation - MD	kgf/15mm	6.5 +/- 1.5	TAPPI T-494	2
5% Elongation - TD	kgf/15mm	20.0 +/- 4.0	TAPPI T-494	2
Tear Strength - MD	gf	150.0 +/- 35.0	TAPPI T-414	2
Tear Strength - TD	gf	60.0 +/- 15.0	TAPPI T-414	2
Clark Stiffness - MD	s-value	150.0 min.	TAPPI T-451	1,2
Clark Stiffness - TD	s-value	280.0 min.	TAPPI T-451	1,2

Notes Key:

- 1 - Stiffness increases with aging over the first month from date of manufacture.
- 2 - Specification range shown

* Yupo test methods based on, but not necessarily the same as, reference stated; Yupo procedure stated if reference not available.

This document provides our current specifications for YPBL250. Changes to these items may occur at the sole discretion of Yupo Corporation America. This issue supersedes any and all previous versions.