

YUPO[®] FEBG095



TECHNICAL DATA SHEET

| Grade | Thickness (μm) | Basis Weight (g/m^2) | Whiteness (%) | Opacity (%) | Gloss (%) | Gloss (%) | Tensile Strength ($\text{kgf}/15\text{mm}$) | | Clark Stiffness (s value) | | Specific Surface Resistance $\log(\Omega/\square)$ | | Yield | |
|-----------------------|--------------------------------|--|------------------|----------------|--------------|--------------|--|-------------|------------------------------|-------------|--|-----------|------------------------|-------------------------|
| | | | | | Top | Back | MD | TD | MD | TD | Top | Back | m^2/kg | ft^2/lb |
| Measurement Method | TAPPI T 411 | TAPPI T 410 | JIS L 1015 | TAPPI T 425 | TAPPI T 480 | TAPPI T 480 | TAPPI T 494 | TAPPI T 494 | TAPPI T 451 | TAPPI T 451 | ASTM D257 | ASTM D257 | | |
| FEBG095 | 95 | 73.2 | 98 | 96 | 49 | 49 | 7.5 | 21.0 | 33.0 | 65.0 | 11 | 11 | 13.7 | 66.7 |

This information is provided for guidance in grade selection and is not a guarantee of performance in a specific application. Changes may occur at the sole discretion of Yupo Corporation America. This issue supersedes any and all previous versions.

Issue date 2022-Oct-14