

YUPO[®] BLR150



TECHNICAL DATA SHEET

Grade	Thickness (μm)	Basis Weight (g/m^2)	Whiteness (%)	Opacity (%)	Gloss (%)	Gloss (%)	Tensile Strength ($\text{kgf}/15\text{mm}$)		Clark Stiffness (s value)		Specific Surface Resistance $\log(\Omega/\square)$		Yield	
					Top	Back	MD	TD	MD	TD	Top	Back	m^2/kg	ft^2/lb
Measurement Method	TAPPI T 411	TAPPI T 410	JIS L 1015	TAPPI T 425	TAPPI T 480	TAPPI T 480	TAPPI T 494	TAPPI T 494	TAPPI T 451	TAPPI T 451	ASTM D257	ASTM D257		
BLR150	150	153.0	93	63	15	15	16.0	40.0	85.0	130.0	---	---	6.5	31.9

This information is provided for guidance in grade selection and is not a guarantee of performance in a specific application. Changes may occur at the sole discretion of Yupo Corporation America. This issue supersedes any and all previous versions.

Issue date 2022-Oct-14